

## BASF Wall Systems | PermaLath®



PRODUCT BULLETIN 1027195

**Description** Open weave, three-dimensional, self-furred, nominal 1/8" thick glass fiber reinforcing lath designed for use with StuccoBase by BASF Construction Chemicals, LLC - Wall Systems (herein after referred to as "BASF Wall Systems") or with other cementitious exterior wall coatings tested in accordance with ICC-ES AC-11 at a maximum thickness of 3/8" to 1/2". Listed in ICC ES ESR-1511. Patent Pending.

**Uses** A component of a 3/8"–1/2" thick exterior cementitious exterior wall coating application that provides keying and continuous reinforcement for stucco used on vertical wall applications with solid backing. Not for use on soffits or open framing.

**Technical Support** Consult the BASF Wall Systems Technical Services Department for specific recommendations concerning all other applications. Consult the BASF Wall Systems website, [www.wallsystems.basf.com](http://www.wallsystems.basf.com) for additional information and for updated literature.

### Technical Data

Weave	Leno
Weight	147 g/m (4.34 oz/yard) ±5%
Min. Tensile Strength	
Warp	35.4 kg/cm (198 lb/inch)
Weft	38.2 kg/cm (214 lb/inch)
Color	Gray

### Packaging

39" x 150 lineal feet roll in poly bag, 7.3 kg (16 lbs.) per roll.

### Features & Benefits

Features	Benefits
Non metallic	Will not rust
Pliable, with no sharp edges	Easier and safer to handle and cut
Non-directional	Can be applied vertically or horizontally
Wide rolls	Fewer overlaps required to give better coverage
Three-dimensional profile	Self-furring, excellent mechanical key using traditional fastening procedures
Alkali resistant	Long-term durability and performance
Packaged in light-weight rolls	Application time/labor savings

## Application

General: Apply PermaLath in accordance with Specifications and the following:

- A.** Acceptable substrates include cement board (ASTM C1325 Type A Exterior), gypsum sheathing (ASTM C79 or C1177), exposure 1 or better exterior grade plywood, exposure 1 OSB, poured concrete or unit masonry. Apply/install substrate per the manufacturer's instructions and applicable building codes. Not for use over open framing.
- B.** Secondary moisture protection barrier (Not required on unit masonry/non-insulated concrete substrates surfaces to receive the cementitious exterior wall coating).
  - 1.** Acceptable secondary moisture protection barriers include polymeric weather resistive barriers such as Tyvek® Stuccowrap® and acceptable equals that comply with and are recognized by local building codes. Grade D and other asphalt saturated building papers must not be used with systems incorporating PermaLath. Trowel/roller-applied weather barriers can be used provided a subsequent layer of a polymeric weather resistive barrier such as Tyvek Stuccowrap or equal is applied over the trowel/roller applied weather barrier.
  - 2.** Install the secondary moisture protection barrier over the substrate according to manufacturer's specifications and applicable building code requirements.
  - 3.** The secondary moisture protection barrier shall be free of any damage such as holes or breaks, and must be applied to all surfaces to receive the cementitious exterior wall coating.
  - 4.** Wrap the secondary moisture protection barrier into rough openings (doors, windows, etc.) to increase the level of protection to the building frame and interior.
  - 5.** Coordinate work with other trades to assure proper sequencing, detailing and installation of materials.
- C.** Trim
  - 1.** Install trim accessories per drawings and specification.
- D.** PermaLath
  - 1.** Apply PermaLath over substrate with minimum 3" overlap at vertical and horizontal edges and overlap on flange of trim accessories. PermaLath can be applied horizontally or vertically and should be applied such that it is flat and free of ripples, wrinkles, etc.
  - 2.** Fasteners: ULP-302 (1 3/4") or Lath Plate (1 1/4") Mechanical Fastening Systems by Wind-lock Corp.
    - a.** Masonry: masonry type [M] expansion fastener with ULP 302 diameter washer; or lath plate 25 mm (1") minimum penetration into masonry. Fastener spacing 6" o.c. vertically and 16" o.c. horizontally.
    - b.** Light Gauge Steel Framing/Furring (20 Gauge): light metal type [LM] bugle head screws with ULP 302 (1 3/4") diameter washer or lath plate 16 mm (5/8") minimum penetration into framing 6" o.c. vertically and 16" o.c. horizontally.
    - c.** Heavy Gauge Steel Framing (18 to 12 Gauge maximum): metal type [S] bugle head screws with ULP 302 (1 3/4") diameter washer or lath plate; 16 mm (5/8") minimum penetration to framing 6" o.c. vertically and 16" o.c. horizontally.
    - d.** Wood framing: wood type [W] bugle head screws with ULP 302 (1 3/4") diameter washer or Lath Plate; 16 mm (5/8") minimum penetration into framing or minimum 16 gauge wire staples with minimum 3/4" crown and minimum 3/4" penetration into framing, 6" o.c. vertically and 16" o.c. horizontally.

**Note:** Supplemental fasteners, into the framing or sheathing, can be used to secure the PermaLath prior to application of cementitious exterior wall coating. Fastening systems/tools for staples are available through Senco ([www.senco.com](http://www.senco.com)) and other manufacturers.
  - 3.** Apply cementitious exterior wall coating within 60 days of PermaLath application.
- E.** Cementitious exterior wall coating
  - 1.** Install per Specifications and Details. Maximum cementitious exterior wall coating thickness is 1/2".
 

**Note:** Recommended method of cementitious exterior wall coating application is double back or scratch and brown. Use of tighter (less water) cementitious exterior wall coating mix in initial double back or scratch coat can ease cementitious exterior wall coating application.

**Shipping,  
Handling &**

- A.** Protect PermaLath during transportation and installation to avoid physical damage.
- B.** Store PermaLath in an upright position in a cool, dry place protected from exposure to moisture. Protect from extreme heat and direct sunlight.

**Limitations**

- A.** Polymeric weather resistive barrier such as Tyvek Stuccowrap required.
- B.** Not for use on soffits or open framing.
- C.** Maximum cementitious exterior wall coating thickness of 1/2".

**Warranty**

BASF Construction Chemicals, LLC, through its Wall Systems Division ("BASF Wall Systems"), warrants that this Product, if used and applied in accordance with BASF Wall System's recommendations set forth, will be free from defects in material for a period of one (1) year from the date of original purchase. BASF Wall Systems will replace or, at BASF Wall Systems' election, refund the purchase price of any portion of this Product proved to be defective. Satisfactory results depend not only upon quality of the Product but also upon factors beyond our control. Except as expressly stated herein, BASF WALL SYSTEMS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, OF ANY KIND WHATSOEVER CONCERNING THE PRODUCT. BASF WALL SYSTEMS EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. BASF WALL SYSTEMS ALSO EXPRESSLY DISCLAIMS, AND WILL NOT BE RESPONSIBLE FOR, ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES. BASF Wall Systems will have no liability if the problem with the Product or apparent defect is attributable to misuse, improper installation or application, alteration or mishandling of the Product. Any claim arising from an alleged Product defect must be received by BASF Wall Systems in writing within thirty (30) days of the date of discovery of the alleged defect or one (1) year from the date of original purchase, whichever is sooner. No claim will be processed or considered unless BASF Wall Systems receives written notice of such claim within the time limitations stated above. User is fully responsible for determining the suitability of the Products for the intended use and assumes all risks and liability in connection therewith. Any authorized change in printed recommendations concerning the use of this Product must bear the signature of the BASF Wall Systems Technical Service Manager.

**Manufacturer**

Permalath™ is manufactured exclusively for BASF Wall Systems by Saint-Gobain Technical Fabrics America, Inc.

**Disclaimer**

BASF Wall Systems is an operating unit of BASF Construction Chemicals, LLC. (herein after referred to as "BASF Wall Systems"). This information and all further technical advice are based on BASF Wall Systems' present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF Wall Systems disclaims any and all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF WALL SYSTEMS SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF Wall Systems reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

**BASF Wall Systems**

3550 St. Johns Bluff Road South  
Jacksonville, FL 32224-2614  
Phone 800 • 221 • 9255  
Fax 904 • 996 • 6300  
[www.wallsystems.basf.com](http://www.wallsystems.basf.com)